

AD-A250 171



Science Center
Rockwell International
1049 Camino Dos Rios
P.O. Box 1085
Thousand Oaks, California 91358
(805) 373-4545



Rockwell
International

DTIC
ELECTE
MAY 13 1992
S C D

April 23, 1992

In reply refer to GO 71033

Scientific Officer
Materials Division
Office of Naval Research
800 No. Quincy Street
Arlington, VA 22217-5000

Attention: Wallace Smith

Subject: Electrodeposition of High Temperature Superconductors
Quarterly R&D Status Report #6
for Period 01/01/92 through 03/31/92
Contract No. N00014-90-C-0225
SC71033.QRDSR

Enclosed please find subject report.

ROCKWELL INTERNATIONAL CORP.
Science Center


D. Morgan Tench
Principal Investigator

cs: Director, Advanced Research
Projects Agency
3701 North Fairfax Drive
Arlington, VA 22203-1714
Attn: DSO/Frank Patten - 1 copy
Scientific Officer - 3 copies

Director,
Naval Research Laboratory
Attn: Code 2627
Washington, DC 20375 - 1 copy

Defense Technical Information Ctr.
Bldg. 5, Cameron Station
Alexandria, VA 22034-6145
- 2 copies

Strategic Analysis
4001 N. Fairfax Drive, No. 765
Arlington, VA 22203
Attn: Mark Davis - 1 copy

Statement A per telecon Dr. Wallace Smith
ONR/Code 1131
Arlington, VA 22217-5000

NWW 5/8/92

15 April 1992

In reply refer to G.O. 71033

Office of Naval Research
800 North Quincy Street
Arlington, VA 22217-5000

Attention: Dr. Wallace A. Smith

Subject: Quarterly R&D Status Report No. 6
"Electrodeposition of High Temperature Superconductors"
For period 01/01/92 through 03/31/91
Contract No. N00014-90-C-0225
SC71033.QRDSR

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	



PROGRAM SUMMARY

The overall objective of this project is to develop a process for direct electrodeposition of Y-Ba-Cu superconducting oxides from a molten salt at relatively low temperatures (300-550°C). The approach entails establishing a sequence of electrochemical steps for the layered deposition of Y, Ba and Cu oxide species from a eutectic Na-K nitrate melt.

PROGRAM STATUS

No work was performed during this reporting period since incremental funding had not been received. An application for a no-cost extension of the program to 09/30/92 was submitted. Incremental funding has recently been received.

ACCOMPLISHMENTS

Not applicable.

PROBLEM AREAS

None.

GOALS FOR NEXT REPORTING PERIOD

Future work will focus on developing and evaluating promising schemes for electrodeposition of Y-Ba-Cu HTSC materials. Initial


92 4 30 001

92-11836



studies will be directed toward evaluating the molten salt electrochemical equivalent of molecular beam epitaxy. In this case, the electrode voltage is maintained just positive of that required for Ba oxide deposition, and monolayer amounts of Cu and Y are injected (by electrodisolution of individual metal electrodes) and electrodeposited in sequence. A cell of very small volume is used to ensure that complete deposition of the injected metal occurs in a short time. Incorporation of Ba oxide layers should occur in proper sequence by underpotential compound formation. This simple straightforward approach will be investigated thoroughly before more complicated deposition schemes are considered.

Rockwell International Science Center

A handwritten signature in cursive script, reading "D. M. Tench". The signature is written in dark ink and is positioned above the printed name and title.

D. M. Tench
Principal Investigator